

# 木浆 & 纤维素纸滤材 Wood pulp & Cellulose filtration paper

各类木浆和纤维素滤纸滤材: Wood pulp and cellulose filtration paper:

> 克重 | Area weight: 90-400g/m<sup>2</sup> 有效去除固体颗粒物范围: 2-65µm Effectively remove particle size: 2-65µm

- 应用市场: 食品加工、食用油过滤、工业油过滤等 Applications: Food & beverage, Edible oil, industrial oil and etc.
- 产品优势 | Advantages:
  滤效稳定,耐用性好,食品级安全。
  Consistent efficiency, Excellent durability, Food grade safety.
  可按客户要求定制加工成品。
  Customize processing service of finished product is available.



## 产品技术参数 | Product Technical Data

#### 1. Wood pulp filter paper

Code Name	Area Weight (g/m²)	Thickness (mm)	Tensile Strength (N/5cm)		Air Permeability (L/m²⋅S)	Precision (μm)	Color
			TD	MD			
MG-M90	90 ± 5	0.2 ± 0.03	≥50	≥100	20-150	2-15	White
MG-M150	$150 \pm 10$	0.55 ± 0.1	≥90	≥120	80-300	8-20	White
MG-M180	$180 \pm 10$	$0.7 \pm 0.1$	≥110	≥150	60-280	10-20	White
MG-M190	$190 \pm 10$	$0.6 \pm 0.1$	≥110	≥240	50-200	5-10	Natural
	$190 \pm 10$	$0.6 \pm 0.1$	≥110	≥240	50-200	5-10	White
MG-M270	$270 \pm 10$	$0.7 \pm 0.1$	≥400	≥400	20-150	2-10	White
MG-M350	350 ± 15	$0.85 \pm 0.1$	≥400	≥400	20-50	1-5	White
MG-M400	400 ± 20	$1.05 \pm 0.1$	≥200	≥250	40-120	3-15	White

2. Cellulose filter paper

Code Name	Area Weight (g/m²)	Thickness (mm)	Tensile Strength (N/5cm)		Air Permeability (L/m²⋅S)	Precision (μm)	Width Range (m)
			TD	MD			
MG-X55	55 ± 3	0.4 ± 0.03	≥123	≥26	2500-3100	45-65	1.5-2
MG-X40	40 ± 3	0.27 ± 0.03	≥95	≥13	2700-3500	30-40	1.5-2

#### 免责声明/Disclaimer

该资料中产品的公开性能参数不属于对产品质量具有法律约束力的声明。 这些性能参数不会成为合同的组成部分。它们代表在制造时根据适用的测试方法获得的平均值, 并受正常生产波动的影响。 产品参数如有更改,恕不另行通知。 如需了解更多产品信息,请联系名冠。

The disclosed performances and measured values of the product in this document are not legally binding statements of product quality. These performances and values will not form part of the contract. They represent average values obtained at the time of manufacture according to applicable test methods and are subject to normal manufacturing variations. The products properties are subject to change without prior notice. Please contact Mingguan for more information.

### 联系方式 / Contact:

上海名冠净化材料股份有限公司 / Shanghai Mingguan Purification Materials Co., Ltd.

上海市闵行区闵虹路 166 弄中庚环球创意中心 T2-2301/2319 室

Room 2301/2319, T2, Lane. 166, Minhong Road, Minhang District, Shanghai 201102, P. R. China

TEL: +86 21 3350 6325 Email: contact@mingguangroup.com